FUD-3564, Revision: A
PM095-1550 LNA-FA Optical Fiber

You have selected an application designed fiber, not fully released which may have a longer lead time than our standard products.

Parameter	Min	Nom	Max	Unit	Compliance
Operating Wavelength	1500		1620	nm	Design
Cladding Attenuation at 1095nm	0		15	dB/km	Measured
Core NA		0.095			Design
Cladding NA (5%)	0.46				Design
Cutoff	1400		1500	nm	Measured
Gaussian MFD at 1550 nm	13.5		14.7	µm	Measured
Customer comment:	Mode Field Diameter at 1550 nm to be the 1/e2 fit of the far field profile (Gaussian), measured on the PK2500 using the variable aperature method.				
Beat Length at 1550 nm	1		5	mm	Measured
Crosstalk at 1550 nm per 100 meters	-100		-30	dB	Measured
Crosstalk at 1550 nm per 5 meters	-100		-40	dB	Measured
Core Diameter		12		µm	Design
Clad Diameter	124		126	µm	Measured
Core/Clad Offset	0		2	µm	Measured
Coating Diameter	230		260	µm	Measured
Coating-Clad Concentricity	0		5	µm	Measured
Prooftest Level	100		120	kpsi	Measured
Operating Temperature Range	-40		85	°C	Design
Bend Loss at 10 cm diameter	0		0.01	dB/m	Measured
Customer comment:	Attenuation measured at 1550 nm on a 10 cm diameter spool with 20 turns to be less than 0.01 dB/m, and will be measured once per lot of fiber.				
Bend Loss at 20 cm diameter	0		5	dB/km	Measured
Customer comment:	Attenuation measured at 1550 nm on a 20 cm diameter spool with 100 turns to be less than 5 dB/km, and will be measured once per lot of fiber.				
Comments	Coating Requirements: Low Index Polymer Coating				

7 Airport Park Road, East Granby, CT 06026 • 860.408.5000 • Toll-free 866.466.0214 • Fax 860.844.0210 • E-mail info @ nufern.com • www.nufern.com •
Nufern products are manufactured under an ISO 9001:2008 certified quality management system.

RoHS