

Polarization Maintaining 1300 nm Telecommunication Fibers

Coherent's Polarization Maintaining Telco fibers are designed for today's most advanced networks. Optimized for use at 1310 nm, these fibers are used in all PM applications for data and telecom. Coherent has applied its unique manufacturing facility and capabilities to this product area and has established leading optical, mechanical and geometrical tolerances. The bend insensitive versions of our fibers offer lowest bend loss and extinction ratios at small bend diameters enabling our customers to reduce package sizes. Available in either 250 or 400 micron coating diameters and prooftested to 200 kpsi, Coherent's PM fibers will meet the demands of all current and future applications.

Typical Applications

- · Pump and source pigtails
- PM patchcords
- Polarization sensitive devices

Features & Benefits

- Tight specifications Highly deterministic results, highest product yield
- High fatigue failure resistance Longest service life
- Bend insensitive Survives application in tight geometries (B version)
- All fiber proof tested to > 200 kpsi Critical for ensuring long term reliability

Optical Specifications	PM1300-XP	PM1300B-XP	PM1300-400	PM1300B-400
Operating Wavelength Core NA Mode Field Diameter Maximum Bend Loss Cutoff Core Attenuation Beat Length Normalized Cross Talk	$1270 - 1625 \text{ nm}$ 0.120 9.3 ± 0.5 µm @ 1300 nm N/A $1210 \pm 60 \text{ nm}$ $\leq 1.0 \text{ dB/km} @ 1300 \text{ nm}$ $\leq 4 \text{ nm} @ 1300 \text{ nm}$ $\leq -40.0 \text{ dB at 4 m} @ 1300$ nm $\leq -30.0 \text{ dB at 100 m} @$ 1200 nm	1270 - 1625 nm 0.120 $9.3 \pm 0.5 \ \mu\text{m} @ 1300 \text{ nm}$ $0.5 \ d\text{B} \text{ at } 1300 \text{ nm}, 25 \text{ mm}$ $\text{OD}, 10 \ \text{turns}$ $1210 \pm 60 \text{ nm}$ $\leq 1.0 \ d\text{B}/\text{km} @ 1300 \text{ nm}$ $\leq 4 \ \text{nm} @ 1300 \text{ nm}$ $\leq -40.0 \ d\text{B} \text{ at } 4 \text{ m} @ 1300 \text{ nm}$ $\leq -30.0 \ d\text{B} \text{ at } 100 \text{ m} @$	1270 - 1625 nm 0.120 $9.3 \pm 0.5 \ \mu\text{m} @ 1300 \text{ nm}$ N/A $1210 \pm 60 \text{ nm}$ $\leq 1.0 \ \text{dB/km} @ 1300 \text{ nm}$ $\leq 4 \ \text{mm} @ 1300 \text{ nm}$ $\leq -40.0 \ \text{dB} \text{ at } 4 \ \text{m} @ 1300 \text{ nm}$ $\leq -30.0 \ \text{dB} \text{ at } 100 \ \text{m} @$ $1200 \ \text{nm}$	1270 - 1625 nm 0.120 $9.3 \pm 0.5 \ \mum @ 1300 \text{ nm}$ $0.5 \ dB at 1300 \text{ nm}, 25 \text{ mm}$ $0D, 10 \ turns$ $1210 \pm 60 \text{ nm}$ $\leq 1.0 \ dB/\text{km} @ 1300 \text{ nm}$ $\leq 4 \ mm @ 1300 \text{ nm}$ $\leq -40.0 \ dB at 4 \ m @ 1300 \text{ nm}$ $\leq -30.0 \ dB at 100 \ m @$ $1200 \ nm$
Bending Cross Talk	1300 nm N/A	1300 nm -30 dB at 1300 nm, 25 mm OD, 10 turns	1300 nm N/A	1300 nm -30 dB at 1300 nm, 25 mm OD, 10 turns
Geometrical & Mechanical Specifications				
Cladding Diameter Core Diameter Coating Diameter Coating Concentricity Core/Clad Offset Coating Material Operating Temperature Range Prooftest Level	125.0 ± 1.0 μm 8.0 μm 245.0 ± 15.0 μm < 5.0 μm ≤ 0.50 μm Acrylate -40 to 85 °C ≥ 200 kpsi (1.4 GN/m²)	125.0 ± 1.0 μm 8.0 μm 245.0 ± 15.0 μm < 5.0 μm ≤ 0.50 μm Acrylate -40 to 85 °C ≥ 200 kpsi (1.4 GN/m²)	125.0 ± 1.0 μm 8.0 μm 400.0 ± 15.0 μm < 10.0 μm ≤ 0.50 μm Acrylate -40 to 85 °C ≥ 200 kpsi (1.4 GN/m²)	125.0 ± 1.0 μm 8.0 μm 400.0 ± 15.0 μm < 10.0 μm ≤ 0.50 μm Acrylate -40 to 85 °C ≥ 200 kpsi (1.4 GN/m²)



Special Core Dopants: SiO2/GeO2.

Nufern • 7 Airport Park Road, East Granby, CT 06026 • 860.408.5000 • Toll-free 866.466.0214 • Fax 860.844.0210 • Email: tech.sales@coherent.com www.coherent.com ; www.shop.coherent.com • Coherent products are manufactured under an ISO 9001:2008 certified quality management system.



Custom developed fiber (FUD) specifications are subject to change without notice. Other configurations such as alternative form factors, optimized cut-off and UV cured color coating may be available. Let us know how Coherent can assist with your requirements.