Polarization Maintaining Low Loss Coupler Fibers



Coherent's broad line of PM fibers now includes PM980C-HP & PM14XXC-HP coupler fibers. Components designed with these new coupler fibers exhibit insertion losses up to one order of magnitude better than was previously possible. These fibers also demonstrate superior polarization control in coupler applications, resulting in increased system and network efficiencies.

Typical Applications

- · Couplers and combiners
- Pump combiners
- · Raman gain modules

Features & Benefits

- Dramatically reduced insertion loss Lower system cost
- High proof test (200kpsi) Low risk of mechanical handling failure
- High fatigue failure resistance Longest service life

Optical Specifications

Operating Wavelength Core NA Mode Field Diameter

Cutoff

Core Attenuation

Specifications

Normalized Cross Talk

Geometrical & Mechanical

Cladding Diameter Core Diameter Coating Diameter Coating Concentricity Core/Clad Offset Coating Material Operating Temperature Range Prooftest Level

PM980C-HP

≤ 2.5 dB/km @ 980 nm

 \leq - 37.0 dB at 2 m @ 980

≤ - 20.0 dB at 100 m @ 980 nm

PM14XXC-HP

970 - 1550 nm 1390 - 1625 nm

0.120 0.125

6.6 ± 1.0 µm @ 980 nm 9.8 ± 0.8 um @ 1450 nm 10.4 ± 0.8 µm @ 1550 nm $900 \pm 70 \text{ nm}$

 $1320 \pm 60 \text{ nm}$

≤ 1.0 dB/km @ 1450 nm ≤ 1.0 dB/km @ 1550 nm

≤ - 37.0 dB at 2 m @ 1550

≤ - 20.0 dB at 100 m @

1550 nm

$125.0 \pm 1.0 \, \mu m$ $125.0 \pm 1.0 \, \mu m$

5.5 µm $8.0 \, \mu m$ $245.0 \pm 15.0 \, \mu m$ $245.0 \pm 15.0 \, \mu m$ $< 5.0 \mu m$ $< 5.0 \ \mu m$ $\leq 0.50 \, \mu m$ ≤ 0.50 µm Acrylate Acrylate -40 to 85 °C -40 to 85 °C

≥ 200 kpsi (1.4 GN/m²) ≥ 200 kpsi (1.4 GN/m²)



