

Pure Silica Core Polarization Maintaining Fibers for UV-VIS Wavelengths



Coherent's industry leading short wavelength pure silica core polarization maintaining fibers have superior waveguide, radiation, and mechanical properties, enabling a large variety of applications in diverse markets. High consistency and extreme end-to-end control of optical properties provide particular advantage in spectrographic and frequency sensitive applications. The pure silica core fiber is optimum for demanding applications in the UV and visible spectrum requiring ultra-low attenuation over longer lengths and where resistance to radiation-induced damage and color center formation are critical. Extended range XP and XP+ versions of PM-S405 offer the broadest operational wavelength range with minimal lot to lot beam divergence variation on the XP+ version.

Typical Applications

- Laser pigtailed
- Spectroscopy
- Sensors
- Bio-medical
- Metrology

Features & Benefits

- Panda-style configuration — Superior optical performance, intrinsically good radiation performance
- Tight specifications — Highly deterministic results, highest product yield
- High proof test — Low risk of mechanical damage and failure
- High fatigue failure resistance — Longest service life
- Pure silica core — Resistance to radiation-induced damage and color center formation

Optical Specifications

	PM-S350-HP	PM-S405-XP	PM-S405-XP+
Operating Wavelength	350 – 460 nm	400 – 680 nm	400 – 680 nm
Core NA	0.120	0.120	0.110
Mode Field Diameter (Gaussian)	2.3 μm @ 350 nm (nominal)	3.3 \pm 0.5 μm @ 405 nm 4.6 \pm 0.5 μm @ 630 nm	3.5 \pm 0.5 μm @ 405 nm 7.5 \pm 1.0 μm @ 630 nm
Cutoff	315 \pm 25 nm	380 \pm 20 nm	380 \pm 20 nm
Core Attenuation	N/A	\leq 30.0 dB/km @ 630 nm \leq 30.0 dB/km @ 488 nm	\leq 50.0 dB/km @ 405 nm \leq 30.0 dB/km @ 630 nm \leq 30.0 dB/km @ 488 nm
Beat Length (nominal)	1.5 mm @ 350 nm	N/A	N/A
Normalized Cross Talk	N/A	\leq -30.0 dB at 10 m @ 630 nm	\leq -30.0 dB at 10 m @ 630 nm
Birefringence	nominal 2.5×10^{-4}	nominal 2×10^{-4}	nominal 2×10^{-4}

Geometrical & Mechanical Specifications

	PM-S350-HP	PM-S405-XP	PM-S405-XP+
Cladding Diameter	125.0 \pm 1.0 μm	125.0 \pm 1.0 μm	125.0 \pm 1.0 μm
Core Diameter	2.5 μm	3 μm	3 μm
Coating Diameter	245.0 \pm 15.0 μm	245.0 \pm 15.0 μm	245.0 \pm 15.0 μm
Coating Concentricity	< 5.0 μm	< 5.0 μm	< 5.0 μm
Core/Clad Offset	\leq 0.50 μm	\leq 0.60 μm	\leq 0.60 μm
Coating Material	Acrylate	Acrylate	Acrylate
Operating Temperature Range	-40 to 85 $^{\circ}\text{C}$	-60 to 85 $^{\circ}\text{C}$	-60 to 85 $^{\circ}\text{C}$
Proof Test Level	\geq 200 kpsi (1.4 GN/m ²)	\geq 200 kpsi (1.4 GN/m ²)	\geq 200 kpsi (1.4 GN/m ²)



Beam Divergence for PM-S405-XP+:
150 \pm 10/-15 mRads @ 405 nm; 140 \pm 10/-20 mRads @ 488 nm; and 115 \pm 10 mRads @ 635 nm

Nufern • 7 Airport Park Road, East Granby, CT 06026 • 860.408.5000 • Toll-free 866.466.0214 • Fax 860.844.0210 • Email: tech.sales@coherent.com
www.coherent.com ; www.shop.coherent.com • Coherent products are manufactured under an ISO 9001:2008 certified quality management system.



Custom developed fiber (FUD) specifications are subject to change without notice. Other configurations such as alternative form factors, optimized cut-off and UV cured color coating may be available. Let us know how Coherent can assist with your requirements.